

CHANG CHUN CHEMICAL(ZHANGZHOU) CO., LTD.

No.1 Baosheng Rd, Jiaomei Town, Taiwanese Investment Zone, Zhangzhou, Fujian, China

TEL : 86-596-6269085 FAX : 86-596- 6269688

Engineering Platics

Polybutylene Terephthalate

PBT 4820NCB

Technical Data

CCP PBT 4820NCB

PBT4820NCB is a glass fiber 20% reinforced injection moulding grade.

PBT 4820NCB 为 20%玻璃纤维强化聚丁烯对苯二甲酸酯复合材料

Characteristics 品质特性

- 1)excellent electrical property 优越的电气性质
- 2)excellent mechanic and chemical property 优越的机械与耐化学特性
- 3)excellent weatherability 耐候性佳
- 4)excellent wear property 耐磨耗性佳
- 5)excellent moldability 优越的成型性
- 6)High resistance to fuels, oil, fats and many solvents 高抗燃料、油料、溶剂特性

Injection Moulding Condition

Cylinder temperatures : 240-270°C

料管温度

Nozzle temperature : 260-270°C

射嘴温度

Mould temperature : 40-120°C, suitable temperature 60-80°C

模温

Injection rate : middle – fast

射速

Screw speed : 60-120 rpm, to be chosen in such a way that plasticizing time is just within cooling time.

螺杆转速

Pressure Injection pressure : 50-120 MPa

压力

射压

Holding pressure : 30-80 MPa

保压

Back pressure : 0-0.3 MPa

背压

Feed tube retention time : ≤2Minute

料管滞留时间

Drying: temperature*time : 120°C*4hr / 140°C*3hr

烘料: 温度*时间

Packaging 包装

25 kg/ paper bag 纸袋包装 25kg

Material handing

Moisture pick-up from ambient air should be avoided. Keep hopper properly closed.

CHANG CHUN CHEMICAL(ZHANGZHOU) CO., LTD.

No.1 Baosheng Rd, Jiaomei Town, Taiwanese Investment Zone, Zhangzhou, Fujian, China

TEL : 86-596-6269085 FAX : 86-596- 6269688

Engineering Plastics Polybutylene Terephthalate

CCP PBT 4820NCB

Property 品质特性	Value 测试值	Unit 单位	Test method 测试方法
Ash 灰份	20	%	
Density 密度	1.52	g/cm ³	ISO 1183
Melting point 熔点	225	°C	ISO 11357
Heat deflection temperature under load 热变形温度 --- 1.8 MPa	205	°C	ISO 75
--- 0.45 MPa	220	°C	ISO 75
Moisture absorption (24h) 吸水率	0.03	%	ISO 15512
Flammability acc. to UL94,3.0 mm thickness (耐燃性)	V-0	-	UL94
Tensile strength 拉伸强度	105	MPa	ISO 527
Tensile elongation 拉伸伸长率	2.5	%	ISO 527
Flexural strength 弯曲强度	160	MPa	ISO 178
Flexural modulus 弯曲模量	6500	MPa	ISO 178
Izod impact strength – notched(moulded-in) 冲击强度	6.5	KJ/m ²	ISO 180
Dielectric strength, 2 mm 绝缘破坏强度	20	KV/mm	IEC 60243
Volume resistivity 体积阻抗率	10 ¹⁵	Ω-cm	IEC 60093
Surface resistivity 表面阻抗率	10 ¹²	Ω	IEC 60093

※表中测试数据为材料典型数据，仅供参考。

(1) For reference only.

(2) All data in the table are the typical values of the material and not the minimum values of the material specifications.